

Continuum in the spin excitation spectrum of a Haldane chain (erratum).

I. A. Zaliznyak¹, S.-H. Lee^{2,3}, S. V. Petrov⁴

¹Department of Physics, Brookhaven National Laboratory, Upton, New York 11973-5000

²National Institute of Standards and Technology, Gaithersburg, Maryland 20899

³Department of Physics, University of Maryland, College Park, Maryland 20742

⁴P. Kapitza Institute for Physical Problems, ul. Kosygina, 2, Moscow, 117334 Russia
(February 2, 2008)

PACS numbers: 75.10.Jm, 75.40.Gb, 75.50.Ee

In Ref. [1] we reported inelastic neutron scattering study of the spin excitation spectrum in the S=1 quasi-one-dimensional antiferromagnet CsNiCl₃. A cross-over from the coherent, single-particle magnon excitation at wavevectors close to $q = \pi$, to a continuum dominated by the two-particle states at small wavevectors, $q \lesssim 0.5\pi$, was clearly demonstrated by the measured intensities shown in the Fig. 2 of that paper. For the sake of comparison, the two-magnon lineshapes predicted from the nonlinear σ -model by Affleck and Weston in Ref. [2] were also shown, by the dotted lines, in the figure.




FIG. 1. Corrected version of the Fig. 2 in Ref. [1]. Dotted lines which show the prediction of Ref. [2] were corrected.

It recently came to our attention that theoretical curves shown in Fig. 2 of our paper [1] are slightly incorrect. This is clear if one compares the onset of the dotted line in Fig. 2 with the 2-magnon boundary shown

in Fig. 3 of the paper, which is at lower energy. The error in Fig. 2 came about because an incorrect value of the Haldane gap, about twice the expected value of $0.41J$, was, by mistake, used for the single-particle dispersion in the formulas of Ref. [2]. As a result, the discrepancy between the prediction of the nonlinear σ -model and the experimental results looks larger than it actually is.

Figure 1 here is the corrected version of the Fig. 2 of Ref. [1], and is now in agreement with the Fig. 3 of that paper. Clearly, there is also much better agreement between the data and the σ -model prediction now (note the absence of an arbitrary intensity scaling). Nevertheless, the observed continuum still lies noticeably *below* the lowest energy of the two non-interacting purely 1D magnons, supporting our previous conclusion that there is an *attraction* between the quasiparticles which form the continuum states [1]. Such attraction is probably a result of the inter-chain coupling which leads to a 3D ordering in CsNiCl₃. On the mean field level it can be understood in a manner similar to the spinon attraction in the coupled S=1/2 chains, if the excitations are the “spin-zero defects” of Ref. [3], as shown in Fig. 2 below.




FIG. 2. Attraction of the $S^z = 0$ defects in the antiferromagnetic background, introduced by the mean field H_{MF} arising from the inter-chain ordering.

We thank Ian Affleck for pointing out this error, and F. Essler for encouraging discussions. This work was carried out under Contract DE-AC02-98CH10886, Division of Materials Sciences, US DOE. The work on SPINS was supported by NSF through DMR-9986442.

-
- [1] I. A. Zaliznyak, S.-H. Lee and S. V. Petrov, Phys. Rev. Lett. **87**, 017202 (2001).
 - [2] I. Affleck, R. A. Weston, Phys. Rev. B **45**, 4667 (1992).
 - [3] G. Gómez-Santos, Phys. Rev. Lett. **63**, 790 (1989).